

RAVENOL Getriebeoel EPX 85W-90 GL-5

Մածուցիկություն: 85W-90

Mineral



1 L

Հոդված:
1223206-001



4 L

Հոդված:
1223206-004



20 L

Հոդված:
1223206-020
Հոդված:
1223206-020-01-999



20 L, ecobox

Հոդված:
1223206-B20
Հոդված:
1223206-B20-01-888



60 L

Հոդված:
1223206-060
Հոդված:
1223206-060-01-999



208 L

Հոդված:
1223206-208
Հոդված:
1223206-208-01-999

In order to avoid the seasonal change of the transmission oil **RAVENOL Getriebeoel EPX SAE 85W-90 GL 5** was developed. It can be used in winter as well as in summer.

RAVENOL Getriebeoel EPX SAE 85W-90 GL5 guarantees due to the balanced additive combination characteristics like a high pressure absorption capacity, a superior viscosity temperature behaviour, a high oxidation stability, low pour points, a good corrosion protection and non-sludging.

Application Note

RAVENOL Getriebeoel EPX SAE 85W-90 GL 5 is compatible with all brand-name transmission oils. No “flushing” required when switching to **RAVENOL Getriebeoel EPX SAE 85W-90 GL 5**.

Use **RAVENOL Getriebeoel EPX SAE 85W-90 GL 5** in hypoid gears for hypoid gearbox, manual transmissions, axle drives, distributor and intermediate transmissions in vehicles and working machines.

Characteristics

- Optimal cold flow property
- Outstanding wear protection even with short trips in winter
- High pressure stable lubrication film, thus outstanding wear protection under any stress
- Reduced transmission noise and the best transmission efficiency under full load, i.e. even with very hot oil.
- Outstanding shearing stability
- Excellent oxidation stability, no foaming
- No oil thickening or deposits
- Extraordinary ageing stability
- Excellent viscosity-temperature properties
- Effective wear protection
- Extraordinary corrosion protection, no rust, won't harm non-ferrous metals
- Neutral to sealants, transmissions stay tight, no oil loss

Բնութագրերը

Մնուն	Իմաստը	Մուդիտ
API	GL-5	
Համապատասխանում է արտադրողի պահանջներին	DTFR 12B100 (MB 235.0), Ford SQ-M2C 9002-AA, MAN 342 Type M1, MB 235.0, MIL-L-2105 D, ZF TE-ML 05A, ZF TE-ML 16B, ZF TE-ML 17B, ZF TE-ML 19B	
Հատուկ հզորություն 20°C-ի դեպքում	882 գ/սմ ³	EN ISO 12185
Գույն	tan	տեսողական
Մածուցիկություն 100 °C-ում	14.3 mm ² /s	DIN 51562-1
Մածուցիկություն 40 °C-ում	130.3 mm ² /s	DIN 51562-1
Մածուցիկության ինդեքս VI	108	DIN ISO 2909
Բրոկֆիլդի մածուցիկություն, -26°C-ում	60.100 mPa*s	ASTM D2983
Բյուրեղացման ջերմաստիճան	-33 °C	DIN ISO 3016
Կառուցման ջերմաստիճան	222 °C	DIN EN ISO 2592
Բրոնզային կոռոզիայի թեստ, 121°C / 3 ժամ	1b	ASTM D130

OEM անալոգներ

Ford

A72SX19K261CA, A72SX19K261DA, 1781297, 5000166, 5000167, 5009922, A82SX19K261AA

Toyota

0888500500, 0888500503

Դադարեցված փաթեթավորում

Փաթեթավորում	Հոդված	Շտրիխ կոդ
4 լ	1223206-004-01-999	
20 լ, ecobox	1223206-B20-01-888	