

RAVENOL Turbo Oil T46

Մածուցիկություն: 46

Mineral



20 L

Հոդված:
1331115-020



60 L

Հոդված:
1331115-060



208 L

Հոդված:
1331115-208
Հոդված:
1331115-208-01-999
Շտրիխ կոդ:
4014835842373



1 000 L

Հոդված:
1331115-700

RAVENOL Turbo Oil T46

is a high quality lubricating oil for gas and steam turbines as well as for turbo compressors with and without gears, which meets the requirements of DIN 51515-2.

RAVENOL Turbo Oil T46

is based on high quality base oils with additives to improve the corrosion protection and resistance to aging.

RAVENOL Turbo Oil T46

is an all-purpose oil for turbines from specially selected base oils with the addition of special refined additives.

Application Note

RAVENOL Turbo Oil T4

is used in stationary gas turbines, steam turbines and also in electrical or in driven by steam machines, such as generators, compressors, pumps and gearboxes.

RAVENOL Turbo Oil T4

is also for use in lubrication of hydraulic systems, compressors, gear transmissions and bearings.

Բնութագրերը

Մնուն	Իմաստը	Մուդիտ
Հաստատված է արտադրողի կողմից	Siemens TLV 9013 04, Siemens TLV 9013 05	
Համապատասխանում է արտադրողի պահանջներին	Alstom HTGD 90117 V0001 S, BS 489, Brown Boveri HTGD 90117, CEGB 207001, General Electric GEK 46568 A, General Electric GEK 46568 C, MIL-L-17672 D, U.S. Steel 20, Westinghouse Turbine Oil Spec.	
Համապատասխանում է արտադրողի բնութագրերին	DIN 51515-1 L-TD, DIN 51515-2 L-TG	
Հատուկ հզորություն 20°C-ի դեպքում	840 գ/սմ ³	EN ISO 12185
Գույն	L1.0	DIN ISO 2049
Մածուցիկություն 40 °C-ում	46.1 mm ² /s	DIN 51562-1
Բյուրեղացման ջերմաստիճան	-12 °C	DIN ISO 3016
Կառուցման ջերմաստիճան	274 °C	DIN EN ISO 2592
Ջրի պարունակություն	0.01 %	DIN 51777-1
Շարքային պինայի մնացորդ 600 s հետո 25°C-ով	0 ml	ISO 6247
Ջրազատություն	75 s	DIN 51589-1
Նեյտրալիզացման համարը	0.06 mg KOH/g	DIN 51558-1
Պինայի ծավալը 25°C-ով	0 ml	ISO 6247
Պինայի փլուզման ժամանակը 25°C-ով	0 s	ISO 6247
Մաքրության աստիճան	20/17/12	ISO 4406
FZG անցումային ծանրաբեռնվածություն	10	DIN ISO 14635-1
Պղնձյա շերտի փորձարկում	pass	DIN EN ISO 2160
Օդի բացթողում 50 °C ջերմաստիճանում, մաքս.	5 min.	DIN ISO 9120

Դադարեցված փաթեթավորում

Փաթեթավորում	Հոդված	Շտրիխ կոդ
20 լ	1331115-020-01-999	